

In Vitro Complex Shear Modulus of Bovine Muscle Tissue (Steak)



Abstract

Dynamic instrumented indentation provides a relevant, accurate and easy way to measure the mechanical properties of soft biological tissue. In this work, we measured the complex shear modulus of bovine muscle tissue submerged in saline, at bovine body temperature (38°C). Along the grain, the direction in which the muscle contracts and relaxes, the shear modulus was 24.4 ± 13.9 kPa. Orthogonal to the grain, the shear modulus was 11.4 ± 2.9 kPa. The loss factor was highly consistent and independent of testing direction: $\tan \delta = 0.34 \pm 0.035$.

Introduction

Being able to measure mechanical properties of soft living tissue is crucial to understanding tissue function, mainly due to the reciprocal relationship that exists between mechanical properties of a tissue and its function. Thus, knowledge of mechanical properties of a tissue can contribute to an understanding of its function. The purpose of this work was to demonstrate the use of instrumented indentation to measure the complex shear modulus of soft tissue under physiological conditions—submerged in saline at body temperature.

We chose bovine muscle tissue (steak) as an exemplary material. Figure 1 shows a schematic of skeletal muscle tissue. The “grain” of the steak runs in the long direction of the muscle tissue; this is the direction in which the muscle contracts and relaxes. A cut across the grain of the steak reveals the same cross-section shown schematically in Figure 1. The proper term for a “grain” is “fascicle,” which is a bundle of individual muscle cells or fibers. Given this structure of muscle tissue, we expect the properties of the tissue to be anisotropic.

Dynamic instrumented indentation returns the stiffness (S) and damping ($C\omega$) of the contact at the prescribed frequency. Using Sneddon’s elastic contact theory² as later developed by Oliver, Pharr, and Brotzen³ and Herbert et al.⁴, the real and imaginary components of the complex shear modulus

$$G^* = G' + iG''$$

are calculated as

$$G' = \frac{S(1-\nu)}{2D}$$

and

$$G'' = \frac{C\omega(1-\nu)}{2D}$$

where ν is the Poisson’s ratio of the material (assumed to be 0.5 for soft tissue) and D is the contact diameter (i.e. the diameter of the punch face). Traditionally, the shear loss modulus (G'') is not reported as an absolute value, but in relation to the shear storage modulus. The loss factor, which characterizes the damping relative to stiffness, is calculated directly as

$$\tan \delta = \frac{G''}{G'} = \frac{C\omega}{S}$$




Figure 2. Steak samples as prepared for testing (a) cut across the grain, and (b) cut with the grain.

Experimental Method

The The KLA Nano Indenter[®] instrument was used for testing. The system was configured with an InForce 50 actuator, the CSM option and the hot-stage option. The CSM option allowed the superposition of an oscillating force, and the hot-stage option allowed the samples to be tested at body temperature. The InForce 50 actuator was fitted with a flat-ended cylindrical punch ($D=101.1\mu\text{m}$) in order to generate a known and constant contact.

Two samples of steak were tested in this work: one cut across the grain (Figure 2a) and one cut with the grain (Figure 2b). Each kind of sample was prepared in the following way: The night before testing, the tissue was rough-cut and frozen. A disk ($\approx 8\text{mm} \times \approx 8\text{mm}$) was cut from the frozen material and quickly adhered to the base of the sample well¹ using 5-minute epoxy. Once the epoxy had set, the well was filled with saline and the sample holder was attached to the hot stage. Finally, a microscope slide was gently laid over the sample to keep it from drying while the sample equilibrated to the testing temperature (38°C). The equilibration time was about 30 minutes. Figure 3 shows a sample ready for testing.

It should be noted that the testing direction is orthogonal to the plane of the cut. Thus, the sample which was cut across the grain (Figure 2a) was actually tested in the direction of the grain—that is, in the direction of the muscle fibers illustrated in Figure 1. The sample that was cut with the grain was actually tested perpendicular to the grain. Results are reported according to the direction of the test, not the cut.

The InView test method with the Biomaterials pack was used for all testing. Each test with this method comprised the following steps:

1. Approach the surface, oscillating the indenter at its natural frequency (110Hz), until contact is detected
2. Switch to the user-prescribed testing frequency (10Hz)
3. Apply pre-test compression ($7\mu\text{m}$)
4. Sense tissue stiffness and damping
5. Withdraw the indenter and move to the next test site




Figure 3. Steak sample, submerged and ready for testing at body temperature. Microscope slide was used to seal the sample and keep it moist until just prior to testing.

¹ In order to allow the samples to be submerged during testing, we used washers to build a “well” on the sample base plate for the hot-stage. Two washers, built up from the base plate with JB Weld SteelStik, provided sufficient depth (8mm).

With this method, twenty-five different sites were tested on each sample; individual test sites were separated by at least $400\mu\text{m}$. Tests were performed in red tissue only. Each test took about two minutes. In order to keep the samples from drying out, testing was paused after every 5 tests in order to add 1–2 drops of saline. Others have solved the problem of drying by integrating an intravenous drip.⁵

Results and Discussion

Testing a sample submerged in saline poses no problems. Although the system indeed senses contact with the saline, the signature is different from that of contact with tissue (Figure 4). The attraction between the tip and the fluid causes a momentary decrease in the stiffness of the system. Thus, the interaction between the tip and the fluid manifests as a slight, but detectable, increase in the phase angle. Subsequent contact with the sample causes an increase in the stiffness of the system, thus manifesting as a sharp decrease in the phase angle. This extreme sensitivity in the phase angle is attained by oscillating the indenter at the natural frequency of the instrument (110Hz) during the approach.

Figure 5 shows the results for shear modulus. The muscle tissue is significantly stiffer in the direction of the grain ($G' = 24.4 \pm 13.9$ kPa) than perpendicular to it ($G' = 11.4 \pm 2.9$ kPa). This is not surprising since the muscle tissue naturally acts in the direction of the grain to alternately exert and relax force.

The point-to-point variation in modulus is high, especially in the direction of the grain, but this is to be expected for biological materials. The observed variation is due to true point-to-point variation in properties, not measurement uncertainty.² Indeed, when we test uniform gels of comparable moduli, the point-to-point variation is quite low.⁶ In the direction of the grain, this high degree of variation is likely due to the complex structure exposed by the cut across the grain (as illustrated by the cross-section of Figure 1). Perpendicular to the grain, the variation is smaller. Again, this is not surprising, because the structure is less complex in this direction.

The uniformity and consistency of the loss factor is quite surprising, however (Figure 6). The ability of the tissue to damp energy, as quantified by the loss factor is rather independent of the direction or location ($\tan\delta = 0.34 \pm 0.035$ for both directions). The value of the loss factor (0.34) means that at 10Hz, the capacity of the tissue to damp energy is one third of its capacity to store energy elastically. This is physiologically realistic and only measurable by keeping the sample submerged during testing.




Figure 4. Signature of contact with saline and tissue.




Figure 6. Loss factor of bovine muscle tissue at 38C, 10Hz (N = 25).

². At 10Hz, the uncertainty in the stiffness measurements taken by the InForce 50 head is less than 0.1N/m. In this work, the contact stiffness measurements were 5–10N/m. Thus, we expect 1–2% variation due to measurement uncertainty.

Conclusions

The values for complex shear modulus measured in this work confirm the anisotropic nature of muscle tissue and provide a reliable basis for relating other comparable measurements. These precise measurements are made possible by key hardware and software features of the KLA Nano Indenter® system. The ability to oscillate the indenter makes the system sensitive to the slightest changes, and the software automatically responds to such changes to direct the progress of the experiment according to the experimenter's prescription. We anticipate that these techniques will be used by others to illuminate fundamental relationships between structure, function and mechanical properties in biological tissues.

Acknowledgement

This work was funded in part by the Bulgarian Ministry of Education, Youth and Science, Human Resources Development Operational Program, Project BG051PO001/3.3-05-0001 "Science and Business".

References

1. Jain, S.K., Bhattacharayya, C.N., Badonia, B., and Singh, R.P., "Study of Unusual Phenomenon of Contact Firing on Gelatine Block Using .38 Special Revolver—Forensic Importance," *Forensic Science International* 133(3), 183–189, 2003.
2. Sneddon, I.N., "The Relation Between Load and Penetration in the Axisymmetric Boussinesq Problem for a Punch of Arbitrary Profile," *Int. J. Eng. Sci.* 3(1), 47–57, 1965.
3. Pharr, G.M., Oliver, W.C., and Brotzen, F.R., "On the Generality of the Relationship among Contact Stiffness, Contact Area, and Elastic-Modulus during Indentation," *Journal of Materials Research* 7(3), 613–617, 1992.

KLA SUPPORT

Maintaining system productivity is an integral part of KLA's yield optimization solution. Efforts in this area include system maintenance, global supply chain management, cost reduction and obsolescence mitigation, system relocation, performance and productivity enhancements, and certified tool resale.

© 2019 KLA Corporation. All brands or product names may be trademarks of their respective companies. KLA reserves the right to change the hardware and/or software specifications without notice.

KLA Corporation
One Technology Drive
Milpitas, CA 95035
www.kla.com

Printed in the USA
2019-01